NC/QC/W-05/2020-21/AL-CB4

Date: 10-07-2020

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 07days Compressive Strength).
{Project*: Development and Improvements of Road, Drain and Covering Slabs at Agrahara Layout in Ward No.05.}

Ref.: Material testing/PMC/21-21,

Report Required for: Assistant Executive Engineer,
Project Division, Yelahanka Zone,
BBMP, Bangalore.

Name of the Agency/Contractor*: Sri. S K Keshavamurthy, Bangalore.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : M_{15}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	03-07-19	10-07-20	07	22500	305	13.56	**13.78**
	002	"	"	"	"	315	14.00	
	003	"	"	"	"	310	13.78	

NEWZEN CONSULTANT BANGALORE

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com

Scanned by TapScanner

Date: 13-07-2020

NC/QC/W-05/2020-21/AL-CB5

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 07days Compressive Strength).
{Project*: Development and Improvements of Road, Drain and Covering Slabs at Agrahara Layout in Ward No.05.}

Ref.: Material testing/PMC/21-21,

Report Required for: Assistant Executive Engineer,
Project Division, Yelahanka Zone,
BBMP, Bangalore.

Name of the Agency/Contractor*: Sri. S K Keshavamurthy, Bangalore.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE

CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : M_{15}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	06-07-19	13-07-20	07	22500	310	13.78	**13.56**
	002	"	"	"	"	305	13.56	
	003	"	"	"	"	300	13.33	

NEWZEN CONSULTANT BANGALORE

Page No. 1/1,

Scanned by TapScanner

NC/QC/W-05/2020-21/AL-CB6

Date: 15-07-2020

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 07days Compressive Strength).
{Project*: Development and Improvements of Road, Drain and Covering Slabs at Agrahara Layout in Ward No.05.}

Ref.: Material testing/PMC/21-21,

Report Required for: Assistant Executive Engineer,
Project Division, Yelahanka Zone,
BBMP, Bangalore.

Name of the Agency/Contractor*: Sri. S K Keshavamurthy, Bangalore.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : M_{15}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	08-07-19	15-07-20	07	22500	320	14.22	**13.93**
	002	"	"	"	"	305	13.56	
	003	"	"	"	"	315	14.00	

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com

Scanned by TapScanner

NC/QC/W-05/2020-21/AL-CB7

Date: 18-07-2020

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 07days Compressive Strength).
{Project*: Development and Improvements of Road, Drain and Covering Slabs at Agrahara Layout in Ward No.05.}

Ref.: Material testing/PMC/21-21,

Report Required for: Assistant Executive Engineer,
Project Division, Yelahanka Zone,
BBMP, Bangalore.

Name of the Agency/Contractor*: Sri. S K Keshavamurthy, Bangalore.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : M_{15}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	11-07-19	18-07-20	07	22500	325	14.44	13.85
	002	"	"	"	"	300	13.33	
	003	"	"	"	"	310	13.78	

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com

Scanned by TapScanner

NEWZEN CONSULTANTS BANGALORE

NEW TECHNOLOGIES TO INNOVATE

NC/W-08/2020-21/AL-CH8

Date: 21-07-2020

TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 07days Compressive Strength).
(Project*: Development and Improvements of Road, Drain and Covering Slabs at Agrahara Layout in Ward No.05.)

Ref: Material testing/PMC/21-21.

Report Required for: Assistant Executive Engineer,
Project Division, Yelahanka Zone,
BBMP, Bangalore.

Name of the Agency/Contractor*: Sri. S K Keshavamurthy, Bangalore.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : M_{15}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	14-07-19	21-07-20	07	22500	305	13.56	13.70
	002	"	"	"	"	320	14.22	
	003	"	"	"	"	300	13.33	

Page No. 1/1,

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com

Scanned by TapScanner

NEWZEN CONSULTANTS BANGALORE

NEW TECHNOLOGIES TO INNOVATE

NC/QC/W-08/2020-21/AL-CB9

Date: 24-07-2020

I. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 07days Compressive Strength).
{Project*: Development and Improvements of Road, Drain and Covering Slabs at Agrahara Layout in Ward No.05.}

Ref.: Material testing/PMC/21-21,

Report Required for: Assistant Executive Engineer,
Project Division, Yelahanka Zone,
BBMP, Bangalore.

Name of the Agency/Contractor*: Sri. S K Keshavamurthy, Bangalore.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE

CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : M_{15}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/ mm^2)	Avg. Value
1	001	17-07-19	24-07-20	07	22500	310	13.78	**13.78**
	002	"	"	"	"	320	14.22	
	003	"	"	"	"	300	13.33	

NEWZEN CONSULTANT * BANGALORE *

Page No. 1/1,

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com

Scanned by TapScanner

NC/QC/W-05/2020-21/AL-CB1a

Date: 21-07-2020

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 28days Compressive Strength).
{Project*: Development and Improvements of Road, Drain and Covering Slabs at Agrahara Layout in Ward No.05.}

Ref.: Material testing/PMC/21-21,

Report Required for: Assistant Executive Engineer,
Project Division, Yelahanka Zone,
BBMP, Bangalore.

Name of the Agency/Contractor*: Sri. S K Keshavamurthy, Bangalore.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE

CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : M_{15}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	23-06-20	21-07-20	28	22500	405	18.00	**17.56**
	002	"	"	"	"	385	17.11	
	003	"	"	"	"	395	17.56	

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com

Scanned by TapScanner

NC/QC/W-05/2020-21/AL-CB2a

Date: 24-07-2020

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 28days Compressive Strength).
{Project*: Development and Improvements of Road, Drain and Covering Slabs at Agrahara Layout in Ward No.05.}

Ref.: Material testing/PMC/21-21,

Report Required for: Assistant Executive Engineer,
Project Division, Yelahanka Zone,
BBMP, Bangalore.

Name of the Agency/Contractor*: Sri. S K Keshavamurthy, Bangalore.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE

CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : M_{15}

TABLE 1.1:

Sl No.	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	26-06-20	24-07-20	28	22500	395	17.56	**17.11**
	002	"	"	"	"	375	16.67	
	003	"	"	"	"	385	17.11	

NEWZEN CONSULTANT BANGALORE

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com

Scanned by TapScanner

Date: 27-07-2020

NC/QC/W-05/2020-21/AL-CB3a

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 28days Compressive Strength).
{Project*: Development and Improvements of Road, Drain and Covering Slabs at Agrahara Layout in Ward No.05.}

Ref.: Material testing/PMC/21-21,
Report Required for: Assistant Executive Engineer,
Project Division, Yelahanka Zone,
BBMP, Bangalore.

Name of the Agency/Contractor*: Sri. S K Keshavamurthy, Bangalore.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE

CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : M_{15}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	29-06-20	27-07-20	28	22500	390	17.33	**17.33**
	002	"	"	"	"	385	17.11	
	003	"	"	"	"	395	17.56	

NEWZEN CONSULTANT BANGALORE

KTR

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com

Scanned by TapScanner

NC/QC/W-05/2020-21/AL-CB4a

Date: 31-07-2020

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 28days Compressive Strength).
{Project*: Development and Improvements of Road, Drain and Covering Slabs at Agrahara Layout in Ward No.05.}

Ref.: Material testing/PMC/21-21,

Report Required for: Assistant Executive Engineer,
Project Division, Yelahanka Zone,
BBMP, Bangalore.

Name of the Agency/Contractor*: Sri. S K Keshavamurthy, Bangalore.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE

CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : M_{15}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	03-07-20	31-07-20	28	22500	405	18.00	**17.70**
	002	"	"	"	"	390	17.33	
	003	"	"	"	"	400	17.78	

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com

Scanned by TapScanner

NC/QC/W-05/2020-21/AL-CB5a

Date: 03-08-2020

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 28days Compressive Strength).
{Project*: Development and Improvements of Road, Drain and Covering Slabs at Agrahara Layout in Ward No.05.}

Ref.: Material testing/PMC/21-21,

Report Required for: Assistant Executive Engineer,
Project Division, Yelahanka Zone,
BBMP, Bangalore.

Name of the Agency/Contractor*: Sri. S K Keshavamurthy, Bangalore.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE

CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : M_{15}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	06-07-20	03-08-20	28	22500	375	16.67	**17.26**
	002	"	"	"	"	390	17.33	
	003	"	"	"	"	400	17.78	

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com

Scanned by TapScanner

NC/QC/W-05/2020-21/AL-CB6a

Date: 05-08-2020

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 28days Compressive Strength).
{Project*: Development and Improvements of Road, Drain and Covering Slabs at Agrahara Layout in Ward No.05.}

Ref.: Material testing/PMC/21-21,

Report Required for: Assistant Executive Engineer,
Project Division, Yelahanka Zone,
BBMP, Bangalore.

Name of the Agency/Contractor*: Sri. S K Keshavamurthy, Bangalore.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE

CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : M_{15}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	08-07-20	05-08-20	28	22500	395	17.56	**17.48**
	002	"	"	"	"	380	16.89	
	003	"	"	"	"	405	18.00	

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com

Scanned by TapScanner

NC/QC/W-05/2020-21/AL-CB7a

Date: 08-08-2020

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 28days Compressive Strength).
{Project*: Development and Improvements of Road, Drain and Covering Slabs at Agrahara Layout in Ward No.05.}

Ref.: Material testing/PMC/21-21,

Report Required for: Assistant Executive Engineer,
Project Division, Yelahanka Zone,
BBMP, Bangalore.

Name of the Agency/Contractor*: Sri. S K Keshavamurthy, Bangalore.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE

CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : M_{15}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	11-07-20	08-08-20	28	22500	405	18.00	**17.56**
	002	"	"	"	"	385	17.11	
	003	"	"	"	"	395	17.56	

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com

Scanned by TapScanner

Date: 11-08-2020

C/QC/W-05/2020-21/AL-CB8a

TEST REPORT ON CEMENT CONCRETE CUBES:

ub: Testing of Concrete Cubes (for 28days Compressive Strength).
{Project*: Development and Improvements of Road, Drain and Covering Slabs at Agrahara Layout in Ward No.05.}

ef.: Material testing/PMC/21-21,
eport Required for: Assistant Executive Engineer,
Project Division, Yelahanka Zone,
BBMP, Bangalore.

Name of the Agency/Contractor*: Sri. S K Keshavamurthy, Bangalore.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE

CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : M_{15}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	14-07-20	11-08-20	28	22500	370	16.44	**17.04**
	002	"	"	"	"	385	17.11	
	003	"	"	"	"	395	17.56	

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com

Scanned by TapScanner

NC/QC/W-05/2020-21/AL-CB9a

Date: 14-08-2020

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 28days Compressive Strength).
{Project*: Development and Improvements of Road, Drain and Covering Slabs at Agrahara Layout in Ward No.05.}

Ref.: Material testing/PMC/21-21,

Report Required for: Assistant Executive Engineer,
Project Division, Yelahanka Zone,
BBMP, Bangalore.

Name of the Agency/Contractor*: Sri. S K Keshavamurthy, Bangalore.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE

CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : M_{15}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	17-07-20	14-08-20	28	22500	400	17.78	**17.85**
	002	"	"	"	"	395	17.56	
	003	"	"	"	"	410	18.22	

NEWZEN CONSULTANT BANGALORE

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com

Scanned by TapScanner